



CURVWOOD®

## Pressure-Sensitive Adhesive (PSA) Veneer

### Technical Specifications

Information provided is based on 4' x 8' sheet

THICKNESS	.025 plus or minus .005
MACHINE SURFACE SAND	150 grit
PACKAGING STANDARD	2 - 10 pcs / 11 - 15 pcs
TYPICAL BOX SIZE	11-3/8" x 11-3/8" x 50" / 13-5/8" x 13-5/8" x 50"
WEIGHT/4X8 SHEETS	4.4 lbs
(Bending Radius) FLEXIBILITY	Approximately 1" (varies with species)
STANDARD SIZE	2' x 8'
MAXIMUM SIZE	4' x 10'

#### Storage:

- Best to store in a climate controlled environment (Heated in winter/Air-conditioned in summer)
- Relative humidity of 35% is best
- Avoid exposure to sunlight

#### Color and Grain Appearance:

- Variation can be expected from sheet to sheet and lot to lot
- Sequence matching available upon request

#### General Application Information:

- Inspect material for satisfaction of quality and grade prior to lamination.
- All veneer should be acclimated prior to application
- Ideal temperature for application is 70° - 80° F
- Ideal humidity is 35%
- Surface must be clean, dry and smooth (free of dust, grease, wax) to ensure a good bond
- Veneer scrapers are recommended for hand application to allow for maximum pressure. "J" rollers are not recommended.
- Adhesive should be allowed to cure for 48 hours prior to finishing